

TEST REPORT



APPLICANT : LG HAUSYS, LTD.

REPORT NO. : M270-17-02800

SAMPLE RECEIVED DATE : 2017-03-07

TEST STARTED DATE : 2017-03-07

REPORT ISSUED DATE : 2017-03-20

PAGE : 1 OF 3

DESCRIPTION : ONE(1) PIECE OF SUBMITTED CUTTING SAID TO BE FLOORING.

=====

ITEM : Z:IN FLOOR DELUXE(2T300)

=====

TEST CONDUCTED : AS REQUESTED BY THE APPLICANT, FOR DETAILS PLEASE SEE ATTACHED PAGES.

=====

PREPARED AND CHECKED BY
FOR FITI



SEONG-KEUN, JANG
QUALITY MANAGER

AUTHORIZED BY
FOR FITI



YOUNG-CHAN KIM
PRESIDENT

※ Report Verification No.: PYQD-YR2R-9KNS ※

(You can see the authenticity of your test report through the above "Report Verification No." at FITI homepage.)

e-DOCUMENT SERVICE

The test results contained in this report are limited to results on the sample(s) that is provided by client and are not necessarily indicative or representative of the qualities of the lot from which the sample(s) was taken or of all products. Results contained in this report are not based on the quality certification of sample by the FITI quality certification program unless specifically requested by the client. Further use of the results of this report is prohibited unless allowed under a separate agreement set forth in an official document that is established between the client identified on this letter and the FITI. This test report is irrelevant to KOLAS accreditation.

REPORT NO.: M270-17-02800

PAGE : 2 OF 3

01. LENGTH (KS M 3802 : 2014) : mm

	#1
	300.1

02. WIDTH (KS M 3802 : 2014) : mm

	#1
	300.1

03. THICKNESS (KS M 3802 : 2014) : mm

	#1
	2.02

04. DETERMINATION OF LOSS ON HEATING (KS M 3802 : 2014) : %

	#1
	0.36

NOTE) TEST CONDITION : (100 ± 3) °C, 6 h

05. LENGTH CHANGE RATIO BY HEATING (KS M 3802 : 2014) : %

	#1
LENGTH	0.04
WIDTH	0.03

NOTE) TEST CONDITION : (80 ± 2) °C, 6 h

06. LENGTH CHANGE BY ABSORPTION (KS M 3802 : 2014) : %

	#1
LENGTH	0.03
WIDTH	0.03

NOTE) TEST CONDITION : (20 ± 2) °C, 120 h

07. DETERMINATION OF INDENTATION (KS M 3802 : 2014) : mm

	#1
20°C	0.18
45°C	0.27

e-DOCUMENT SERVICE

The test results contained in this report are limited to results on the sample(s) that is provided by client and are not necessarily indicative or representative of the qualities of the lot from which the sample(s) was taken or of all products. Results contained in this report are not based on the quality certification of sample by the FITI quality certification program unless specifically requested by the client. Further use of the results of this report is prohibited unless allowed under a separate agreement set forth in an official document that is established between the client identified on this letter and the FITI. This test report is irrelevant to KOLAS accreditation.

REPORT NO.: M270-17-02800

PAGE : 3 OF 3

08. RESIDUAL INDENTATION (KS M 3802 : 2014) : %

	#1
	7.5

09. SQUARENESS (KS M 3802 : 2014) : mm

	#1
	0.04

10. ABRASION RESISTANCE (ASTM D4060:14, TABER METHOD) : WEIGHT LOSS, mg

	#1
	204.0

NOTE) ABRADANT TYPE : CS-17, APPLIED WEIGHT : 1 000 g, TEST CYCLES : 1 000 CYCLES
WEIGHT LOSS AFTER 1 000 CYCLES ABRASION

11. STAIN TEST (KS M 3802 : 2014) : APPEARANCE

	#1
CEMENT PASTE	NO CHANGE SUCH AS DISCOLORATION, GLOSS LOSS, SWELLING
5 % ACETIC ACID	NO CHANGE SUCH AS DISCOLORATION, GLOSS LOSS, SWELLING
5 % HCl	NO CHANGE SUCH AS DISCOLORATION, GLOSS LOSS, SWELLING
SOY SAUCE	NO CHANGE SUCH AS DISCOLORATION, GLOSS LOSS, SWELLING

**** End of The Report ****



e-DOCUMENT SERVICE

The test results contained in this report are limited to results on the sample(s) that is provided by client and are not necessarily indicative or representative of the qualities of the lot from which the sample(s) was taken or of all products. Results contained in this report are not based on the quality certification of sample by the FITI quality certification program unless specifically requested by the client. Further use of the results of this report is prohibited unless allowed under a separate agreement set forth in an official document that is established between the client identified on this letter and the FITI. This test report is irrelevant to KOLAS accreditation.

TEST REPORT



APPLICANT : LG HAUSYS, LTD.

REPORT NO. : M270-18-05823

SAMPLE RECEIVED DATE : 2018-05-04

TEST STARTED DATE : 2018-05-04

REPORT ISSUED DATE : 2018-05-23

PAGE : 1 OF 4

DESCRIPTION : ONE(1) PIECE OF SUBMITTED CUTTING SAID TO BE FLOORING.

=====

ITEM : Z:IN FLOOR DELUXE 3T(300)

=====

TEST CONDUCTED : AS REQUESTED BY THE APPLICANT, FOR DETAILS PLEASE SEE ATTACHED PAGES.

=====

PREPARED AND CHECKED BY
FOR FITI



SEONG-KEUN JANG
QUALITY MANAGER

AUTHORIZED BY
FOR FITI



JE-GOO JUN
PRESIDENT

※ Report Verification No.: JN15-5TW2-3V8B ※

(You can see the authenticity of your test report through the above "Report Verification No." at FITI homepage.)

e-DOCUMENT SERVICE

The test results contained in this report are limited to results on the sample(s) that is provided by client and are not necessarily indicative or representative of the qualities of the lot from which the sample(s) was taken or of all products. Results contained in this report are not based on the quality certification of sample by the FITI quality certification program unless specifically requested by the client. Further use of the results of this report is prohibited unless allowed under a separate agreement set forth in an official document that is established between the client identified on this letter and the FITI. This test report is irrelevant to KOLAS accreditation.

REPORT NO.: M270-18-05823

PAGE : 2 OF 4

01. LENGTH (KS M 3802 : 2014) : mm

	#1
	300.1

02. WIDTH (KS M 3802 : 2014) : mm

	#1
	300.1

03. THICKNESS (KS M 3802 : 2014) : mm

	#1
	3.01

04. SQUARENESS (KS M 3802 : 2014) : mm

	#1
	0.04

05. INDENTATION (KS M 3802 : 2014) : mm

	#1
20 °C	0.19
45 °C	0.45

06. RESIDUAL INDENTATION (KS M 3802 : 2014) : %

	#1
	4.23

07. WEIGHT LOSS ON HEATING (KS M 3802 : 2014) : %

	#1
	0.06

e-DOCUMENT SERVICE

The test results contained in this report are limited to results on the sample(s) that is provided by client and are not necessarily indicative or representative of the qualities of the lot from which the sample(s) was taken or of all products. Results contained in this report are not based on the quality certification of sample by the FITI quality certification program unless specifically requested by the client. Further use of the results of this report is prohibited unless allowed under a separate agreement set forth in an official document that is established between the client identified on this letter and the FITI. This test report is irrelevant to KOLAS accreditation.

REPORT NO.: M270-18-05823

PAGE : 3 OF 4

08. DIMENSIONAL CHANGE TO HIGH TEMPERATURE ON HEAT (KS M 3802 : 2014) : %

	#1
LENGTH	0.03
WIDTH	0.03

09. LENGTH CHANGE BY ABSORPTION (KS M 3802 : 2014) : %

	#1
LENGTH	0.03
WIDTH	0.03

10. ABRASION RESISTANCE (ASTM D 4060 - 2014, TABER METHOD) : mg

	#1
	321

NOTE) TEST CONDITION - ABRADANT TYPE : CS-17,
APPLIED WEIGHT : 1 000 g,
TEST CYCLE : 1 000 CYCLES
MEASURED WEIGHT LOSS AFTER 1 000 CYCLES ABRASION BY THE CLIENT'S REQUEST.

11. STAIN TEST (KS M 3802 : 2014)

	#1
CEMENT PASTE	NO CHANGE SUCH AS DISCOLORATION, GLOSS LOSS, SWELLING
5 % ACETIC ACID	NO CHANGE SUCH AS DISCOLORATION, GLOSS LOSS, SWELLING
5 % HCl	NO CHANGE SUCH AS DISCOLORATION, GLOSS LOSS, SWELLING
SOY SAUCE	NO CHANGE SUCH AS DISCOLORATION, GLOSS LOSS, SWELLING

**** End of The Report ****


e-DOCUMENT SERVICE

The test results contained in this report are limited to results on the sample(s) that is provided by client and are not necessarily indicative or representative of the qualities of the lot from which the sample(s) was taken or of all products. Results contained in this report are not based on the quality certification of sample by the FITI quality certification program unless specifically requested by the client. Further use of the results of this report is prohibited unless allowed under a separate agreement set forth in an official document that is established between the client identified on this letter and the FITI. This test report is irrelevant to KOLAS accreditation.

REPORT NO.: M270-18-05823

PAGE : 4 OF 4

- SAMPLE PHOTO -



e-DOCUMENT SERVICE

The test results contained in this report are limited to results on the sample(s) that is provided by client and are not necessarily indicative or representative of the qualities of the lot from which the sample(s) was taken or of all products. Results contained in this report are not based on the quality certification of sample by the FITI quality certification program unless specifically requested by the client. Further use of the results of this report is prohibited unless allowed under a separate agreement set forth in an official document that is established between the client identified on this letter and the FITI. This test report is irrelevant to KOLAS accreditation.

TEST REPORT



APPLICANT : LG HAUSYS, LTD.

REPORT NO. : M270-18-05818

SAMPLE RECEIVED DATE : 2018-05-04

TEST STARTED DATE : 2018-05-04

REPORT ISSUED DATE : 2018-05-23

PAGE : 1 OF 4

DESCRIPTION : ONE(1) PIECE OF SUBMITTED CUTTING SAID TO BE FLOORING.

=====

ITEM : Z:IN FLOOR DELUXE 3T(450)

=====

TEST CONDUCTED : AS REQUESTED BY THE APPLICANT, FOR DETAILS PLEASE SEE ATTACHED PAGES.

=====

PREPARED AND CHECKED BY
FOR FITI



SEONG-KEUN JANG
QUALITY MANAGER

AUTHORIZED BY
FOR FITI



JE-GOO JUN
PRESIDENT

※ Report Verification No.: K81B-JVNI-BAPZ ※

(You can see the authenticity of your test report through the above "Report Verification No." at FITI homepage.)

e-DOCUMENT SERVICE

The test results contained in this report are limited to results on the sample(s) that is provided by client and are not necessarily indicative or representative of the qualities of the lot from which the sample(s) was taken or of all products. Results contained in this report are not based on the quality certification of sample by the FITI quality certification program unless specifically requested by the client. Further use of the results of this report is prohibited unless allowed under a separate agreement set forth in an official document that is established between the client identified on this letter and the FITI. This test report is irrelevant to KOLAS accreditation.

REPORT NO.: M270-18-05818

PAGE : 2 OF 4

01. LENGTH (KS M 3802 : 2014) : mm

	#1
	450.1

02. WIDTH (KS M 3802 : 2014) : mm

	#1
	450.1

03. THICKNESS (KS M 3802 : 2014) : mm

	#1
	3.01

04. SQUARENESS (KS M 3802 : 2014) : mm

	#1
	0.04

05. INDENTATION (KS M 3802 : 2014) : mm

	#1
20 °C	0.25
45 °C	0.37

06. RESIDUAL INDENTATION (KS M 3802 : 2014) : %

	#1
	2.03

07. WEIGHT LOSS ON HEATING (KS M 3802 : 2014) : %

	#1
	0.04

e-DOCUMENT SERVICE

The test results contained in this report are limited to results on the sample(s) that is provided by client and are not necessarily indicative or representative of the qualities of the lot from which the sample(s) was taken or of all products. Results contained in this report are not based on the quality certification of sample by the FITI quality certification program unless specifically requested by the client. Further use of the results of this report is prohibited unless allowed under a separate agreement set forth in an official document that is established between the client identified on this letter and the FITI. This test report is irrelevant to KOLAS accreditation.

REPORT NO.: M270-18-05818

PAGE : 3 OF 4

08. DIMENSIONAL CHANGE TO HIGH TEMPERATURE ON HEAT (KS M 3802 : 2014) : %

	#1
LENGTH	0.02
WIDTH	0.02

09. LENGTH CHANGE BY ABSORPTION (KS M 3802 : 2014) : %

	#1
LENGTH	0.03
WIDTH	0.02

10. ABRASION RESISTANCE (ASTM D 4060 : 2014, TABER METHOD) : mg

	#1
	290

NOTE) TEST CONDITION - ABRADANT TYPE : CS-17,
APPLIED WEIGHT : 1 000 g,
TEST CYCLE : 1 000 CYCLES
MEASURED WEIGHT LOSS AFTER 1 000 CYCLES ABRASION BY THE CLIENT'S REQUEST.

11. STAIN TEST (KS M 3802 : 2014) : APPEARANCE


	#1
CEMENT PASTE	NO CHANGE SUCH AS DISCOLORATION, GLOSS LOSS, SWELLING
5 % ACETIC ACID	NO CHANGE SUCH AS DISCOLORATION, GLOSS LOSS, SWELLING
5 % HCl	NO CHANGE SUCH AS DISCOLORATION, GLOSS LOSS, SWELLING
SOY SAUCE	NO CHANGE SUCH AS DISCOLORATION, GLOSS LOSS, SWELLING

**** End of The Report ****

e-DOCUMENT SERVICE

The test results contained in this report are limited to results on the sample(s) that is provided by client and are not necessarily indicative or representative of the qualities of the lot from which the sample(s) was taken or of all products. Results contained in this report are not based on the quality certification of sample by the FITI quality certification program unless specifically requested by the client. Further use of the results of this report is prohibited unless allowed under a separate agreement set forth in an official document that is established between the client identified on this letter and the FITI. This test report is irrelevant to KOLAS accreditation.

REPORT NO.: M270-18-05818
PAGE : 4 OF 4



e-DOCUMENT SERVICE

The test results contained in this report are limited to results on the sample(s) that is provided by client and are not necessarily indicative or representative of the qualities of the lot from which the sample(s) was taken or of all products. Results contained in this report are not based on the quality certification of sample by the FITI quality certification program unless specifically requested by the client. Further use of the results of this report is prohibited unless allowed under a separate agreement set forth in an official document that is established between the client identified on this letter and the FITI. This test report is irrelevant to KOLAS accreditation.