

# TFI Report 460281-01

## Testing of Resilient Floor Coverings

### Customer

LG Hausys Ltd.  
One IFC, 20 Yeouido-gong, Yeongdeungpo-gu  
150-876 Seoul  
SOUTH KOREA

### Product

resilient floor covering  
Allroad 1

### Responsible at TFI

Dipl.-Ing. Cornelia Radine  
Tel: +49 241 9679 150  
[c.radine@tfi-online.de](mailto:c.radine@tfi-online.de)

This report includes 2 pages and 1 annex(es)

Aachen, 6 April 2016

**Dr. Ernst Schröder**



The present document is provided with a qualified electronic signature and is valid without autograph signature.

This report only applies to the tested specimens and has been established to the best of our knowledge. Only the entire report shall be reproduced. Under no circumstances, extracts shall be used. Furthermore, we apply the "General Terms and Conditions for the Execution of Contracts" of the Textiles & Flooring Institute GmbH, also with regard to the order execution.

## 1 Transaction

Test order	Length, width and straightness of sheet according to ISO 24341:2012
Order date	23 February 2016
Your reference	Dan BI
Product designation	Allroad 1
TFI sample number	16-02-0064
Date of sample receipt	9 February 2016

## 2 Product Specification

Use surface	PVC *
Construction	homogeneous
Structure	flat
Pattern	plain without pattern
Colour of the use surface	grey
Type of delivery	sheet flooring
	*customer information

## 3 Results

Effective width	2000 mm
-----------------	---------

## 4 Annexes

Width, Thickness and Mass <sup>a</sup> BDM 460281-01

The annexes marked <sup>a</sup> are based on tests accredited in accordance with EN ISO/IEC 17025.

# Annex BDM – Width, Thickness and Mass

## 1 Transaction

Product designation Allroad 1  
TFI sample number 16-02-0064  
Testing period 21 March 2016 – 1 April 2016

## 2 Test Method / Requirements

ISO 24341:2012\* Determination of length, width and straightness of sheet

\*The test was performed by an authorized subcontractor.

## 3 Results

Test	Parameter	Result
ISO 24341:2012	average width [mm]	2001.8
	effective width [mm]	2000

Comments: none