



## TEST REPORT

No. : SHCCM160200562

Date : Mar. 16, 2016

Page: 1 of 2

LG HAUSYS

10 GOOKJEGEUMYOONG-RO, YEONGDEUNGPO-GU, SEOUL 150-876, KOREA

The following sample(s) was/ were submitted and identified on behalf of the client as:

Sample Name : MEDISTEP ALLROAD  
Sample Number : SHCCM160200562  
Test Required : Dimensional stability and curling after exposure to heat  
Test Method : EN ISO 23999:2012  
Product specification : 2.0mm\*2m\*20m  
Buyer : LG HAUSYS  
Manufacture : LG HAUSYS  
Date of Receipt : Feb. 22, 2016  
Test Period : Feb. 22, 2016 to Mar. 16, 2016  
Test result(s) : For further details, please refer to the following page(s)

\*\*\*\*\* To be continued\*\*\*\*\*

Signed for SGS-CSTC Standards  
Technical Services (Shanghai) Co., Ltd.

Erin Huang  
Authorized signatory



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.  
**Attention: To check the authenticity of testing/inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com**  
No.69, Block 1159, East Kang Qiao Road, Pudong District, Shanghai, China. 201319 t(86-21) 61196300 f(86-21) 61191853/68183920 www.sgs.com.cn  
中国·上海·浦东康桥东路1159弄69号 邮编:201319 t(86-21) 61196300 f(86-21) 61191853/68183920 e sgs.china@sgs.com

Member of the SGS Group (SGS SA)

## TEST REPORT

No. : SHCCM160200562

Date : Mar. 16, 2016

Page: 2 of 2

Lab environmental condition: 23±2℃, 50±5%RH

Test result:

Test item	Test method	Test result	
Dimensional stability and curling after exposure to heat	EN ISO 23999:2012	Dimensional change (%)	Manufacturing direction: 0.36 Across-manufacturing direction: 0.06
		Curling (mm)	0
Remark	Specimen dimension: 240mm×240mm×2mm,3pcs. Test specimens were cut from the original sample. Heating temperature: 80℃ Heating time: 6h		

Statement: Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.

Sample photo:



The original sample

\*\*\*\*\* End of report \*\*\*\*\*