

TFI Report 440893-08

Testing of Resilient Floor Coverings

Customer

LG Hausys Ltd.
One IFC, 20 Yeouido-gong, Yeongdeungpo-gu
150-876 Seoul
SOUTH KOREA

Product

Resilient floor covering
DECOCLICK

Responsible at TFI

B. Sc. Katharina Keulen
Tel: +49 241 9679 151
k.keulen@tfi-online.de

This report includes 2 pages and 1 annex(es)

Aachen, 4 09 2014



Dr. Ernst Schröder

The present document is provided with a qualified electronic signature and is valid without autograph signature.

This report only applies to the tested specimens and has been established to the best of our knowledge. Only the entire report shall be reproduced. Under no circumstances, extracts shall be used. Furthermore, we apply the "General Terms and Conditions for the Execution of Contracts" of the Textiles & Flooring Institute GmbH, also with regard to the order execution.

1 Transaction

Test order	Mass per unit area according to ISO 23997:2012
Order date	13 June 2014
Your reference	Dan Bi
Product designation	DECOCLICK
TFI sample number	14-06-0095

2 Product Specification

Use surface	PVC*
Construction	heterogeneous
Structure	embossed*
Pattern	patterned
Colour of the use surface	brown, dark brown, black
Type of delivery	planks
	*customer information

3 Results

Mass per unit area [g/m ²]	6820
--	------

4 Annexes

Width, Thickness and Mass	BDM 440893-08
---------------------------	---------------

The annexes marked ^a are based on tests accredited in accordance with EN ISO/IEC 17025.

Annex BDM – Width, Thickness and Mass

1 Transaction

Product designation DECOCLICK
TFI sample number 14-06-0095
Testing period 30 June 2014 – 30 June 2014

2 Test Method / Requirements

ISO 23997:2012 Determination of mass per unit area
Deviations None
Climate for conditioning and testing According to the standards, deviations see above

*The test was performed by an authorized subcontractor.

3 Results

Test	Parameter	Result
ISO 23997:2012	mass per unit area [g/m ²]	6820

Comments: none